# Technical Data



# DRY MOLY DRY MOLYBDENUM DISULPHIDE LUBRICANT

**AMBERSIL DRY MOLY** is a resin bonded, high pressure resistant, dry film lubricant containing Molybdenum Disulphide for metal-to-metal lubrication where a wet film cannot be tolerated. Once applied, the  $MoS_2$  lubricant prevents seizing, fretting, scuffing and reduces friction. The thin film also helps prevent corrosion and repels water.

#### **APPLICATIONS**

Use for the assembly and running in of components to reduce fretting and scuffing where a wet film cannot be used. Apply to threaded and close tolerance components to prevent seizing and aide assembly and disassembly. Particularly effective where high load bearing surface to surface contact is present.

- Mounting of longitudinal press fits (e.g. bolts and bearing seats)
- Assembly of screws and seals
- Surface treatment of rolling and sliding bearings to improve running-in
- · Lubrication of guides and joints
- Bearing lubrication for wheel bearings and kiln carts
- Lubrication of open gears
- For use where a wet-film lubricant is undesirable

# **DIRECTIONS FOR USE**

- Shake can well (1-2 minutes) until agitator ball is free.
- Ensure application surface is clean, dry, and free from grease, oil and contaminants.
- Hold can upright and spray a thin, even coating from about 25cm away.
- Resin will be touch-dry after 2 3 minutes, and ready for use after approximately 2 hours.
- Lightly polish the cured film with a soft, lint-free cloth to improve performance.

#### **TECHNICAL DATA**

Appearance : Thin, opaque black film

Odour : Ketone solvent

Molybdenum Disulphide

Content (dry film)

: 80%

SG @ 20°C : 0.620

Pressure @ 25°C : 4 bar

Discharge rate : 1.1 g/sec

Operating Temp. Range : -150°C to +400°C

Flammability : Classified as Extremely Flammable under

current EC Regulations

Packaging : 400ml aerosol

## **STORAGE**

The product may be stored at normal ambient temperatures and has a shelf life of not less than 72 months with correct storage. Aerosols should always be stored below  $50^{\circ}$ C, away from direct heat and naked flame.

#### **HEALTH AND SAFETY**

Health and Safety sheet available separately.

#### TECHNICAL SERVICE

CRC Industries UK Ltd provides a technical support service and maintains a constant programme of research and development. We are able to assist customers by specific product development to meet particular requirements.

## MISREPRESENTATION ACT 1967 TRADE DESCRIPTIONS ACT 1968

The information given in this publication is based on our experience and reports from customers. There are many factors outside our control and knowledge which affect the use and performance of our products and for which reason no warranty is given, express or implied. Users should make their own tests to determine the applicability of such information or the suitability of any products for their own particular purposes. Statements concerning the use of the products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is to be assumed.

CRC Industries UK Limited, Wylds Road, Bridgwater, Somerset, TA6 4DD

Tel: +44 (0) 1278 727200 Fax: +44 (0) 1278 425644

Web: www.ambersil.com E-mail: sales.uk@crcind.com

Version: 2