




# Chemical Sorbents

Technical Data Sheet



## Use

For control of spills of hazardous liquids.

## Product Description

3M Chemical Sorbents are made from inert, synthetic fibres principally of polypropylene. They are available in a wide range of formats and are lightweight and dust free. They have a high absorption capacity which minimises the amount of waste for disposal.

## Colour

Yellow - highly visible

## Selection Guide

- **Minibooms:** For surrounding / containment of spills. Prevents further spreading of the spill.
- **Pillows:** For absorption of the bulk volume of a spill. Also useful for plugging holes.
- **Sheets / Rolls:** For fast coverage and absorption of spills. Rolls can be torn to the required length. Both formats can be used to wipe up the final residue of liquid once the bulk has been absorbed.
- **Particulate:** For fast coverage and absorption of spills.
- **Multiformat:** Combines four formats in one product. It can be used as booms, pillows, sheets or rolls.
- **Hazardous spill response kits:** Each contain a selected variety of 3M Chemical Sorbents. Available in five configurations (please refer to the table), these convenient kits assist with providing fast and effective containment and clean-up of hazardous chemical spills.

## Absorption / Sorbency

The case sorbency quoted in the table is based on the American Standard Test Method (ASTM) F726-81 using a medium viscosity fluid (20 weight motor oil).

Another method of measuring absorbent performance is by calculating the *sorbency ratio*. This is the ratio of liquid weight absorbed to the dry absorbent weight.

$$\text{Sorbency} = \frac{\text{wet weight} - \text{dry weight}}{\text{dry weight}}$$

The sorbency ratio and speed of absorption depend upon the ambient temperature, the polarity of the liquid, its surface tension and viscosity. For 3M Chemical Sorbents the sorbency ratio is 10-15 for most liquids.

## Physical Data

Number	Size (cm)	No./ Case	Case Sorbency (litres)	Case Weight (Kg)
<b>Sheets</b>				
P110	28 x 33	200	50	6.5
<b>Rolls</b>				
P130	33 x 3000	2	50	6.0
P190	48 x 3000	2	72	8.6
<b>Pillows</b>				
P300	18 x 38	16	32	3.3
<b>Minibooms</b>				
P200	7.5ø x 120	12	45	5.5
<b>Particulate</b>				
P500	(5.4Kg)	-	54	5.4
<b>Multiformat</b>				
P-F2001	12 x 1520 (40)	3	119	8.2

## Spill Kits

- **Product N° HSRK360 - Absorbency: 360 l**  
**Contain:** 300 Sheets P110, 24 Pillows P300, 24 Minibooms P200, 1 Roll P190, 3 Multiformat P-F2001, 20 Disposable Bags + Ties, 1 Drain Protector, 1 Warning Sign, 1 Warning Tape
- **Product N° HSRK210 - Absorbency: 210 l**  
**Contain:** 100 Sheets P110, 12 Pillows P300, 12 Minibooms P200, 1 Rolls P190, 2 Multiformat P-F2001, 10 Disposable Bags + Ties, 1 Drain Protector, 1 Warning Sign, 1 Warning Tape
- **Product N° HSRK75 - Absorbency: 75 l**  
**Contain:** 100 Sheets P110, 12 Pillows P300, 8 Minibooms P200, 5 Disposable Bags + Ties
- **Product N° HSRK26 - Absorbency: 26 l**  
**Contain:** 10 Sheets P110, 5 Pillows P300, 5 Minibooms P200, 2 Disposable Bags + Ties
- **Product N° HSRK 5 - Absorbency: 5 l**  
**Contain:** 10 Sheets P110, 1 Pillow P300, 1 Disposable Bag + Ties

## Typical Liquids Absorbed

Chemical sorbents are suitable for absorbing a very wide range of liquids. The following list has been compiled based upon 3M tests as an indication of absorbency with major chemical groups. This is by no means exhaustive, and 3M recommends that a sample of sorbents should be tested with any liquid not listed.

# Chemical Sorbents

Chemical	Sorbency
<b>Acids</b>	
Acetic acid (glacial)	10
Hydrofluoric 48%	12
Phosphoric 86%	17
Sulphuric 50%	14
Nitric (concentrated)	12
Nitric (diluted)	11
Hydrochloric 15%	14
<b>Hydrocarbons / Oils</b>	
Fuel oil number 2	9
Oil SAE 20W-50	10
Mineral Oil	8
Peanut Oil	9
<b>Ketones</b>	
Acetone	8
Methy Ethyl Ketone	12
<b>Alcohols</b>	
Ethanol	8
<b>Alkalis</b>	
Sodium Hydroxide 1N 40g / l	10
Sodium Hydroxide 7N	6
Sodium Hydroxide 10N	2
Ammonium Hydroxide 35% NH <sub>3</sub>	15
<b>Aromatic</b>	
Toluene	10
Benzene	11
Ethylbenzene	12
Styrene	13
<b>Chlorinated Solvents</b>	
Carbon Tetrachloride	18
Methalene Chloride	13
1,1,1, Trichloroethane	11
Trichlorotrifluoroethane	13
Trichloroethylene	13
Tetrachloroethylene	15
<b>Glycols</b>	
Dipropylene Glycol	11
Propylene Glycol	11
Diethylene Glycol	2
Polyglycol E200	3
Polyglycol E300	3
Polyglycol E400	3
<b>Others</b>	
Hydrazine	10
Hydrogen Peroxide 6%	9
Ethyl Acetate	7
Antifreeze	10
Water	10
Cutting Fluid	10
Machine Coolant	10

## Limitations of Use

Do not use 3M Chemical Sorbents with the following concentrated chemicals as there is a risk of degradation: Oleum, Chlorosulphonic acid, Liquid bromine, Fuming nitric acid, Chromic acid, Sulphuric acid and Hydrogen peroxide. 3M recommends that a compatibility test be carried out prior to using the absorbent with the liquid concerned. For use in temperatures over 60°C it is essential that such a compatibility test is made prior to use.

## Precautions

3M Chemical Sorbents are not in themselves hazardous products, however, they take on the characteristics of the liquids they absorb. Adequate precautions should be taken when handling or storing hazardous / inflammable materials and appropriate personal protective equipment should be worn. Users should be informed of the risks incurred in use, storage and disposal of used sorbents.

## Disposal

Dispose of used sorbents only in accordance with local and national regulations. Disposal companies should be consulted for their recommendations. Options may include incineration and landfilling depending on regulations.

## Waste Minimisation

3M recommends that waste streams should wherever possible be minimised. 3M sorbents promote minimisation by only being a small part of the total waste. In addition, where laws allow, 3M Chemical Sorbents can be disposed of by incineration yielding less than 0.02% ash (ASTM D-482). The high energy value of the sorbents (46,000 KJ / Kg) is also favourable for incineration and waste-to-fuel systems. Furthermore, 3M sorbents may be wrung out and reused (90% recovery using mechanical wringing according to ASTM F726-81). The recovered liquid may itself then be reused or disposed of.

## Flammability

3M sorbents have been tested by an independent test house for flammability characteristics. Tests were carried out on longterm storage, heat build-up and ignition from three sources: spark, flame and cigarette using oil and diesel at 0%, 50% and 100% saturation levels. Tests were compared to testing on clay granules and sawdust. The results which are available in a full report can be summarised: "3M sorbents take on the properties of the liquid absorbed and do not present a greatly increased flammability hazard over other common absorbents. No heat build-up occurs in longterm storage".



### 3M Occupational Health & Environmental Safety

#### 3M United Kingdom PLC

3M Centre  
Cain Road, Bracknell  
Berkshire RG12 8HT  
Tel: 0870 60 800 60  
www.3m.com/uk/ohes

#### 3M Ireland

3M House, Adelphi Centre Upper Georges St.  
Dun Laoghaire  
Co. Dublin, Ireland  
Tel: 1 800 320 500